

DO 200


Highly breathable membrane
Riweqa | eternitycomfort

Technical data sheet

of 06/02/2014

Art. 02010200 / TOP SK 02020314

Rev.05 of 30/06/2021

Material	PP.PP.PP	 EN 13859 - 1
Film	PP	
Colour	Grey	
Durability under integrated FTV	No	
Roll width / length	1,5 m / 50 m	
Roll weight	15 Kg	
Classification in accordance with UNI 11470 (IT)	A	
Classification in accordance with ZVDH (DE)	UDB-A - USB-A	
Classification in accordance with Önorm B4119/B3661 (A)	Typ I	
Classification in accordance with SIA 232-1 (CH)	UD EB-NB	
Conforms to DTU (FR)	40.29	
Available in TOP SK version	Art. 02020314	

PROPERTIES	METHOD	UNITS	NOMINAL VALUE
Areal mass	EN 1849-2	g/m ²	200 (± 10 g/m ²)
Air layer equivalent to the vapour passage [Sd]	EN 1931 / EN ISO 12572	m	0,02 (-0,01/+0,04)
Water vapour diffusion [DVA]	EN ISO 12572	g/m ² / 24h	ca.1000
Water column	EN 20811	cm	>200
Heavy rain test	TU Berlin	-	Passed
Resistance to water penetration	EN 1928 (Met. A)	-	W1
Tensile strength MD*	EN 12311-1	N/50mm	480 (± 30%)
Tensile strength CD*	EN 12311-1	N/50mm	330 (± 30%)
Elongation MD*	EN 12311-1	%	75 (± 30%)
Elongation CD*	EN 12311-1	%	120 (± 30%)
Resistance to tearing MD*	EN 12310-1	N	260 (± 20%)
Resistance to tearing CD*	EN 12310-1	N	360 (± 20%)
Fire reaction	EN 13501-1	Class	E
UV-stability	-	Months	3
Temperature resistance	-	°C	-40 / +90
After artificial ageing			
Resistance to water penetration	EN 1928 (Met. A)	-	npd**
Tensile strength MD*	EN 12311-1	N/50mm	npd**
Elongation MD*	EN 12311-1	%	npd**

Density	EN 1849-1	Kg/m ³	250
Thickness	EN 1849-2	mm	0,8
Vapour resistance coefficient [μ]	EN ISO 12572	-	25
Vapour permeability coefficient	-	Kg/m*s*Pa	7,72*10 ⁻¹²
Thermal conductivity [λ]	-	W/mK	0,22
Specific heat	-	J/KgK	1700

* MD= Machine Direction; CD= Cross Direction.

**npd= no performance determined

Riweqa S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riweqa.com.
This data sheet replaces the previous copy.