

# Primer Bitum

Water based  
Riwega | eternitycomfort

Technical data sheet  
of: 06/02/2014  
Art. 02040601  
Rev.05 of: 17/12/2024

Properties	
Material	Bitumen in aqueous emulsion and additives
Appearance	Brown fluid
Contents	5 liters
Density at 20°C	(0,99÷1,05) kg/L
Yield (depends on the surface)	Approx. 100÷250 g/m <sup>2</sup>
Working temperature	+5°C / +35°C
Dry residue	(32÷36) %
pH at 20°C	8,0÷11,0
Drying time	20÷40 minutes*
Packaging	1 can
Storage	Dry, in the original container, max. 24 months

\* Values recorded at a temperature of 23°C and 50% humidity. The data expressed may vary depending on the thickness of the product applied and specific site conditions: temperature, humidity, ventilation, absorbency of the substrate.

Riwega S.r.l. reserves the possibility to review or change this document. The updated document can be found on the website [www.riwega.com](http://www.riwega.com). This document replaces the previous version.