

# Sil Butyl

Universal butyl toluene-free sealant  
Riwega | eternitycomfort

Technical data sheet  
of: 06/02/2014  
Art. 02040406-02040407  
Rev.04 of: 16/08/2021

Properties	Cartridge	Tube
Article	02040406	02040407
Material	Butyl glue	
Content	310 ml	600 ml
Minimum width of layer to apply	10-15 mm	
Minimum thickness of layer to apply	6 mm	
Density	Approx. 1,65 g/cm <sup>3</sup> (DIN EN ISO 1183-1)	
Average yield	Approx. 10 m	Approx. 20 m
Working temperature	+5°C / +40°C	
Operating temperature	-40°C / +90°C	
Hardness (Shore A)	Approx. 15 (DIN EN ISO 868)	
Resistance to atmospheric agents	Stable in all climatic zones	
Volumetric variation	10% (DIN EN ISO 9046) / 7,5% (DIN EN 15651-1)	
Viscosity	Stable (DIN EN ISO 7390)	
Skin formation (23°C, 50% RH)	Approx. 1 h	
Inflammability classification	B2 (DIN 4102)	
Reaction to fire	E (DIN EN 13501)	
Cleaning	Freshly applied, can be removed using petrol or turpentine	
Colour	Grey	
Packaging	20 cartridges of 310 ml	20 tube of 600 ml
Storage	Cool and dry place, at temperatures between +15 °C e +25 °C, away from UV rays, max. 12 months	

Riwega S.r.l. reserves the possibility to review or change this document. The updated document can be found on the website [www.riwega.com](http://www.riwega.com). This document replaces the previous version.