

USB Micro 100/20

Vapour control layer
Riwega | eternitycomfort

Technical data sheet
of 28/01/2014
Art. 02030143 / 020301430
Rev.11 of 19/02/2024

Material	PP.PE			
Film	PE			
Colour	Semitransparent white			
Roll width	1,5 m	3,0 m	EN 13984	
Roll length	50 m			
Roll weight	8 Kg	15 Kg		
Classification in accordance with UNI 11470 (IT)	D			
Classification in accordance with Önorm B4119/B3661 (A) Typ I	Typ I			
Classification in accordance with SIA 232-1 (CH)	VU			
Conforms to DTU (FR)	31.2			
Available in TOP SK version	-			

PROPERTIES	METHOD	UNITS	NOMINAL VALUE
Areal mass	EN 1849-2	g/m ²	100 (±10g/m ²)
Air layer equivalent to the vapour passage [Sd]	EN ISO 12572	m	20
Water vapour diffusion [DVA]	EN ISO 12572	g/m ² / 24h	ca. 1,5
Water column	EN 20811	cm	> 400
Resistance to water penetration	EN 13984 (EN1928 Met.A)	-	Passed
Tensile strength MD*	EN 12311-1	N/50mm	180 (±30N/50mm)
Tensile strength CD*	EN 12311-1	N/50mm	120 (±30N/50mm)
Elongation MD*	EN 12311-1	%	65 (±15%)
Elongation CD*	EN 12311-1	%	70 (±15%)
Resistance to tearing MD*	EN 12310-1	N	80 (±15N)
Resistance to tearing CD*	EN 12310-1	N	90 (±15N)
Fire reaction	EN 13501-1	Class	E
UV-stability	-	Months	4
Temperature resistance	-	°C	-40 / +100
Durability			
Artificial ageing	EN 1926	-	Passed
Alkali resistance	EN 13984 (EN1928 Met.A)	-	Passed

Density	EN 1849-1	Kg/m ³	238
Thickness	EN 1849-2	mm	0,42
Vapour resistance coefficient [μ]	EN ISO 12572	-	47619
Vapour permeability coefficient	-	Kg/m*s*Pa	0,0041*10-12
Thermal conductivity [λ]	-	W/mK	0,22
Specific heat	-	J/KgK	1700

* MD= Machine Direction; CD= Cross Direction.

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riwega.com.
This data sheet replaces the previous copy.