

USB Micro Light



QUICK OVERVIEW: STRENGTHS

The lightweight and handy solution for the inside

- Vapour control layer
- Ideal to be laid as inside protection of the wooden wall or ceiling structure
- Easy to be laid thanks to its semi-transparency
- Regulates the passage of vapour and guarantees a perfect wind-tight building envelope

Features:




Classification:



Technical data sheet

Material	PP.PE.PP	
Film	PE	
Colour	Beige	
Mass per unit area	EN 1849-2	120 g/m ²
Thickness		0,57 mm
Sd value	EN ISO 12572	10 m
Water vapour permeability	EN ISO 12572	~ 3 g/m ² /24 h
Water column	EN 20811	>400 cm
Water tightness	EN 13984	passed
Tensile strength MD/CD*	EN 12311-1	210 / 160 N/50mm
Elongation MD/CD*	EN 12311-1	60 / 80 %
Tear resistance MD/CD*	EN 12310-1	180 / 220 N
Fire reaction class	EN 13501-1	E
UV stability		4 months
Temperature resistance		-40°/+100°C

*MD = longitudinal CD = transversal
Riwega Srl is not responsible for negligent and improper use of its products



Composition:

- Protective UV stabilized, water repellent layer in PP ①
- Functional film in PE ②
- Protective layer in PP ③

Codes and measures

Code	Code TOP SK	Width (m)	Length (m)	Pallet (m ²)
02030115	-	1,5	50	1500
020301150	-	3,0	50	3000