

DS 188 ALU


38

R2

QUICK OVERVIEW: STRENGTHS

The most performing vapour barrier with reflecting effect

- Vapour barrier
- In counter-walls and false-ceilings the reflecting surface increases the internal heat reflection
- High mechanical resistance thanks to its reinforcing mesh
- Minimizes the passage of water vapour and guarantees a perfect airtight building envelope



Composition:

- ① Aluminium film
- ② PET reinforcing mesh
- ③ Film in PE

Codes and measures

Code	Code TOP SK	Width (m)	Length (m)	Pallet (m ²)
02064008	-	1,5	50	3000

Features:



Classification:



Technical data sheet

Material	Reinforced PE.Alu	
Colour	Aluminium	
Mass per unit area	EN 1849-2	170 g/m ²
Thickness		0,30 mm
Sd value	EN ISO 12572	200 m
Water vapour permeability	EN ISO 12572	~ 0,2 g/m ² /24 h
Water column	EN 20811	-
Water tightness	EN 13984	passed
Tensile strength MD/CD*	EN 12311-1	290 / 260 N/50mm
Elongation MD/CD*	EN 12311-1	15 / 15 %
Tear resistance MD/CD*	EN 12310-1	180 / 180 N
Fire reaction class	EN 13501-1	E
UV stability		-
Temperature resistance		-40°/+80°C

*MD = longitudinal CD = transversal

Riwega Srl is not responsible for negligent and improper use of its products