

Top Seal



QUICK OVERVIEW: STRENGTHS

The liquid nail sealing

- Nail sealing in a cartridge
- Equipped with a special nozzle for a homogeneous and fast laying
- Guarantees air-, wind- and water tightness of the breathable membranes
- Excellent value for money

Features:



Classification:



Technical data sheet

Material		1-Kwet cross-linked polyurethane
Viscosity (20°C)		~1500 mPa.s
Density (20°C)	EN 542	~1,15 g/cm ³
Formation of skin (20°C)		~12 min.
Partial hardening (20°C/50% UR)		~24 h
Total hardening (20°C/50% UR)		~7 d
Output		~20 g/m
Working temperature sigillante		+7°C / +30°C
Working temperature ambiente		from -5°C
Storage place		dry, protected from UV rays, max. 25°C
Storage period		max. 12 months



Codes and measures

Version	Code	Content (ml)	Box (pc)	Pallet (box)
Cartridge	020450042	1000	10	64
Nozzle FD	020450043	-	1	-