

FDB EXT VSK 350 FL

Acrylic adhesive tape / EXTERNAL USE
Riwega | eteritycomfort

Technical data sheet
of: 13/10/2022
Art. 02046135
Rev.02 of: 29/05/2024

Characteristic	Method	
Adhesive		Modified polyacrylate
Adhesive support		Combination of PP + PP
Liner		Film with Fingerlift, precut to:
		15 mm 167,5 mm 167,5 mm
Roll width		350 mm
Film weight	EN 1849-2	80 g/m ² (±10 g/m ²)
Total weight (incl. liner)	EN 1849-2	380 g/m ² (±20 g/m ²)
Adhesive weight	EN 1849-2	210 g/m ² (±10 g/m ²)
Roll length		25 m
Colour		Anthracite
Thickness	EN 1849-2	0,5 mm (±0,1mm)
Maximum permissible total deformation		5% (in the area of the unconstrained tape width, otherwise an expansion reserve must be provided)
Tensile strength MD*	EN 12311-1	250 N/50mm (±30 N/50mm)
Tensile strength CD*	EN 12311-1	120 N/50mm (120/180 N/50mm)
Elongation MD*	EN 12311-1	90% (±25%)
Elongation CD*	EN 12311-1	150 % (±30%)
Sd value	EN 1931 / EN 12572	ca.0.05m
Airtightness	EN 1026	$a_n \leq 0,1 \text{ m}^3/\text{m}^2\text{h}$
Resistance to water penetration	EN 13984 / EN 1928	W1 Water column > 2000 mm
Working temperature		-10°C / +40°C
Temperature resistance		-40°C / +80°C
Fire reaction class	EN ISO 11925-2: 2010	Class E
Hazardous substances	EU 1907-2006	none
UV-stability**		3 months
Packaging		1 roll
Storage		Store in a cool and dry place, in the original package for max. 12 months

* MD= Machine Direction; CD= Cross Direction

**Referring to the Central Europe climate