

FDB EXT



QUICK OVERVIEW: STRENGTHS

The perfect external sealing of window and door

- Breathable adhesive tape
- Outside use
- Windtight sealing of door and window joints
- Overplasterable surface
- Available in several types to ensure tightness on every laying surface

Features:



Classification:



Composition:

Multilayer non-woven PET.PP.PET ①

Butylic strip / acrylic strip ②

Silicone liner ③

Codes and measures

Version	Code	Measures (mmxm)	Box (pc)	Pallet (box)
FDB EXT AC 75	02045612	75x30	5	96
FDB EXT AC+AC 75	02045622	75x30	5	96
FDB EXT AC+BU 75	02045632	75x25	5	96
FDB EXT AC+BU 100	02045633	100x25	4	96
FDB EXT AC+BU 150	02045634	150x25	2	96

FDB EXT AC 100/150 mm and FDB EXT AC+AC 100/150 mm available on request

Technical data sheet

Glue		acrylic/butylic
Glue carrier material		PET.PP.PET
Thickness	DIN 53855	0,37 mm
S _d value	EN ISO 12572	0,04 m
Resistance to water passage	EN 1928	W1
Tensile strength MD/CD*	EN 12311-1	290 / 31 N/50mm
Elongation at break MD/CD*	EN 12311-1	19 / 130 %
Fire reaction class	EN 13501-1	E
Working temperature		+5°C / +40°C
Temperature resistance		-40°C / +80°C
UV stability		3 months
Storage place		dry, protected from UV rays
Storage period		max. 12 months

*MD = longitudinal CD = transversal

Riwega Srl is not responsible for negligent and improper use of its products