

FDB EXT FL

Acrylic adhesive tape / EXTERNAL USE
Riwega | eternitycomfort

Technical data sheet
of: 13/10/2022
Art. 02046108 / 02046110
02046115 / 02046135
Rev. 04 of: 23/06/2026

Characteristic	Norma	FDB EXT FL 75	FDB EXT FL 100	FDB EXT FL 150	FDB EXT FL 350
Article		02046108	02046110	02046115	02046135
Adhesive		Modified polyacrylate			
Adhesive support		Combination of PP + PP			
Colour		Anthracite			
Liner		Film with Fingerlift, precut to:			
		25 + 50 mm	25 + 75 mm	25 + 60 + 65 mm	15+167,5+167,5mm
Roll width		75 mm	100 mm	150 mm	350 mm
Roll lenght		25 m			
Total weight (incl. Liner)	EN 1849-2	380 g/m ² (± 20 g/m ²)			
Adhesive weight	EN 1849-2	210 g/m ² (± 10 g/m ²)			
Film weight	EN 1849-2	80 g/m ² (± 10 g/m ²)			
Thicknes	EN 1849-2	0,5 mm (± 0,1 mm)			
Tensile strenght MD*	EN 12311-1	250 N/50mm (± 30 N/50mm)			
Tensile strenght CD*	EN 12311-1	120 N/50mm (± 20 N/50mm)			
Elongation MD*	EN 12311-1	90 % (± 25%)			
Elongation CD*	EN 12311-1	150 % (± 30%)			
Resistance to water penetration	EN 1928 Meth. A	W1			
Water column		> 2000 mm			
Airtightness	EN 1026	a _n ≤ 0,1 m ³ /m ² h			
S _d value	EN 1931 / EN 12572	Ca. 0,05 m			
Fire reaction class	EN ISO 13501-1	Class E			
UV-stability		24 Weeks**			
Temperature resistance		- 40°C / +80°C			
Working temperature		- 10°C / +40°C			
Hazardous substances	EU1907:2006	None			
Packaging		5 (5 x 25 m= 125 m)	4 (4 x 25 m= 100 m)	2 (2 x 25 m= 50 m)	1 (1 x 25 m= 25 m)
Storage		12 months, cool and dry place, in the original package.			

*MD= Machine direction; CD= Cross direction / **referring to the Central Europe climate

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riwega.com.
This data sheet replaces the previous copy.