

FDB INT FL

Acrylic adhesive tape / INTERNAL USE
Riwega | eternitycomfort

Technical data sheet
of: 21/09/2023
Art. 02046208 / 02046210
02046215 / 02046250
Rev. 04 of: 23/06/2026



Characteristic	Method	FDB INT FL 75	FDB INT FL 100	FDB INT FL 150	FDB INT FL 350
Article		02046208	02046210	02046215	02046250
Adhesive		Modified polyacrylate			
Adhesive support		Combination of PP + PE			
Colour		Pink			
Liner		Film with Fingerlift, precut to:			
		25 + 50 mm	25 + 75 mm	25 + 60 + 65 mm	15+167,5+167,5mm
Roll width		75 mm	100 mm	150 mm	350 mm
Roll length		25 m			
Total weight (incl. Liner)	EN 1849-2	400 g/m ² (± 20 g/m ²)			
Adhesive weight	EN 1849-2	210 g/m ² (± 10 g/m ²)			
Film weight	EN 1849-2	120 g/m ² (± 10 g/m ²)			
Thickness	EN 1849-2	0,4 mm (± 0,1 mm)			
Tensile strength MD*	EN 12311-1	200 N/50mm (± 20 N/50mm)			
Tensile strength CD*	EN 12311-1	120 N/50mm (± 20 N/50mm)			
Elongation MD*	EN 12311-1	140 % (± 20%)			
Elongation CD*	EN 12311-1	180 % (± 20%)			
Resistance to water penetration	EN 1928 Meth. A	W1			
Water column		> 2000 mm			
Airtightness	EN 1026	a _n ≤ 0,1 m ³ /m ² h			
S _d value	EN 1931 / EN 12572	Ca. 40 m			
Fire reaction class	EN ISO 13501-1	Class E			
UV-stability		12 Weeks**			
Temperature resistance		- 40°C / +80°C			
Working temperature		- 5°C / +40°C			
Hazardous substances	EU1907:2006	None			
Packaging		5 (5 x 25 m= 125 m)	4 (4 x 25 m= 100 m)	2 (2 x 25 m= 50 m)	1 (1 x 25 m= 25 m)
Storage		12 months, cool and dry place, in the original package.			

*MD= Machine direction; CD= Cross direction / **referring to the Central Europe climate

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website www.riwega.com.
This data sheet replaces the previous copy.